

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-138316

(43)Date of publication of application : 14.05.2003

(51)Int.Cl.

C21D 8/10

// C22C 38/00

C22C 38/14

C22C 38/16

(21)Application number : 2002-267058

(71)Applicant : NKK CORP

(22)Date of filing : 07.06.1996

(72)Inventor : TOYODA SHUNSUKE
MITSUTSUJI HARUO
OMURA MASAKI

(30)Priority

Priority number : 07143207

Priority date : 09.06.1995

Priority country : JP

07201172

07.08.1995


JP

(54) METHOD OF PRODUCING ULTRAHIGH TENSILE STRENGTH ELECTRIC RESISTANCE WELDED TUBE

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a method of producing an ultrahigh tensile strength electric resistance welded tube which has high tensile strength, and excellent hydrogen delayed fracture resistance, and moreover excellent corrosion resistance as well.

SOLUTION: A steel slab having a composition containing, by weight, 0.10 to 0.19% C, 0.01 to 0.5% Si, 0.8 to 2.2% Mn, 0.01 to 0.06% Al, 0.005 to 0.03% Nb and 0.0005 to 0.0030% B, and in which the content of P is controlled to $\leq 0.02\%$, S to $\leq 0.003\%$, N to $\leq 0.004\%$, and Ti to $\leq 0.015\%$ is soaked at 1,150 to 1,300°C, is thereafter hot-rolled at a finishing temperature of an Ar3 or higher, and is coiled at 500 to 650°C into a hot rolled steel strip. The steel strip is pickled and cold-rolled, is



thereafter soaked and heated at 800 to 900°C and is rapidly cooled after that in a continuous annealing furnace, and is further subjected to tempering treatment at 150 to 250°C. This steel strip is made into a tube at a width drawing rate Q satisfying $1,000 \leq Q/(t/D) \leq 3,000$ to obtain the ultrahigh tensile strength electric resistance welded tube; wherein, $Q = \{ \pi(D-t) \times 100 / t \}$ (mm) is the sheet thickness, and D (mm) is the outside diameter of the steel tube.